



EUCLID CHEMICAL

EUUCO QWIKJOINT UVR

UV-RESISTANT POLYUREA FLOOR JOINT FILLER

DESCRIPTION

EUUCO QWIKJOINT UVR represents a new generation of polyurea technology with features and benefits unlike any other polyurea joint filler on the market. EUUCO QWIKjoint UVR resists fading from ultraviolet light greater than any existing product. It is a fast-setting, semi-rigid polyurea, primarily used for filling construction and control joints in industrial and commercial concrete floors. EUUCO QWIKjoint UVR can be shaved flush with the floor shortly after placement or up to 24 hours later. EUUCO QWIKjoint UVR supports and protects joint edges from heavy loads and wheel traffic, reducing spalling of the joint edges. EUUCO QWIKjoint UVR is available in 33 standard colors and in a Neutral Base, that can be colored on site with EUCLID UNIVERSAL COLOR PACKS; available in the same 33 colors.

PRIMARY APPLICATIONS

- Concrete construction & control joints
- Crack and joint repair for old floors
- Industrial and commercial floors
- Freezer floors

FEATURES/BENEFITS

- Unparalleled UV resistance
- Fast setting formula reduces downtime
- Large shave-time window allows for greater flexibility in scheduling joint filling operations
- Tough performance reduces floor joint repairs and maintenance
- Will cure in temperatures as low as -20° F (-29°C)
- No bubbles/foaming when used in damp joints
- Less moisture-sensitive than standard polyureas
- Available in 33 standard colors

TECHNICAL INFORMATION

PROPERTY	TEST METHOD	RESULT
Gel Time	--	28 seconds
Shore D Hardness	ASTM D2240	33
Shore A Hardness	ASTM D2240	84
Tensile Strength @ 14 days	ASTM D638	1,290 psi (8.9 MPa)
Elongation at Break @ 14 days	ASTM D638	249%
Shave "Window"	--	1 to 24 hours
Tack-Free Time	--	3 to 4 minutes
Traffic Ready Time	--	Light Traffic: 1 hour Heavy Traffic: 2 hours
Adhesion to Concrete	ASTM D4541	250 psi @ 7 days
Viscosity	ASTM D2196	Part A: 2,000 cp Part B: 1,800 cp

CHEMICAL RESISTANCE, ASTM D 1308

Acetic Acid, 10%	no effect
Alcohol, 10%	no effect
Ammonium Hydroxide, 10%	no effect
Brake Fluid	swelled, softened
Diesel Fuel	discolored
Ethylene Glycol (antifreeze)	no effect
Gasoline	stained
Hydrochloric Acid, 20%	slight swelling
JP-4 Jet Fuel	no effect
Used Motor Oil	stained
Salt Water	no effect
Sodium Hydroxide, 10%	slightly discolored
Sulfuric Acid, 10%	no effect
Xylene	no effect

Appearance: EUUCO QWIKjoint UVR is available in 33 standard colors and in a Neutral Base that can be colored on site using EUCLID UNIVERSAL COLOR PACKS, which are available in the same 33 standard colors. See the EUCLID UNIVERSAL COLOR CHART for available colors. The user should expect some batch to batch variability in color. If possible, "box" the Part B after pre-stirring each pail to ensure color uniformity.

PACKAGING

EUUCO QWIKjoint UVR is a two-component product packaged in 22 oz (600 mL) side-by-side cartridges (12/case) and 10 gal (37.9 L) kits for all 33 standard colors. The mix ratio for all packaging sizes is 1:1.

SHELF LIFE

1 year in original, unopened containers

SPECIFICATIONS/COMPLIANCES

- EUCO QWIKjoint UVR complies with ACI 302 performance recommendations regarding control and construction joint fillers
- USDA

COVERAGE

The following table gives guidelines on theoretical material estimates in linear ft/gal (liner m/L).

Joint Width	Joint Depth		
	1.5"(38 mm)	2"(51 mm)	2.5"(63 mm)
3/16" (4.8 mm)	68 ft (5.5 m)	51 ft (4.2 m)	41 ft (3.2 m)
1/4" (6.4 mm)	51 ft (4.2 m)	38 ft (3.2 m)	30 ft (2.4 m)
3/8" (9.5 mm)	34 ft (2.6 m)	25 ft (2.1 m)	20 ft (1.6 m)

DIRECTIONS FOR USE

Surface Preparation: All joints to be filled must be clean and dry. All oil, dirt, debris, paint and any other material that may be a bond breaker must be removed. The final step in cleaning must be the complete removal of all residue with a vacuum cleaner and oil-free compressed air. All joint facings must possess an open surface texture with all curing compounds and sealers removed. If this product will be used for filling floor cracks, the cracks must be routed out and cleaned before filling. For proper installation, all edges must be squared off.

Joint Backing: To provide proper load transfer, EUCO QWIKjoint UVR must be filled full depth of the joint or crack. Do not use backer rod or other fill material for the purpose of reducing volume. Dried silica sand, 1/16" to 1/8" (1.5 to 3 mm), may be used to fill the crack at the bottom of the joint and prevent three-sided adhesion.

Priming: EUCO QWIKjoint UVR does not require a primer before application.

Mixing: Due to its extremely fast set time, EUCO QWIKjoint UVR requires machine mixing and placing. ****Slowly pre-mix Part B separately before using with a slow speed drill and mixing paddle for 2 to 3 minutes.** Do not whip air into the Part B while mixing. Follow mechanical pump manufacturer's equipment instructions for operation. QWIKjoint UVR cartridges must be shaken before using, as some settlement is normal during storage. Follow the specific installation instructions on the cartridge label.

NOTE: If EUCO QWIKjoint UVR is to be stored in the dispensing pump overnight, place a sheet of plastic wrap directly on top of the liquid material in each tank to prevent exposure to air.

Euclid Universal Color Packs: EUCO QWIKjoint UVR Neutral Base can be colored using 1 EUCLID UNIVERSAL COLOR PACK (EUCO Pack) per 10 gal (37.85 L) unit. Prior to mixing the unit together, stir the color pack into the part "B" side of the product while conducting the pre-mix as described above, until it is fully dispersed. EUCLID UNIVERSAL COLOR PACKS are available in 33 standard colors, see EUCLID UNIVERSAL COLOR CHART for available colors.

Placement: EUCO QWIKjoint UVR must be installed in the joint full depth. Joints should be slightly overfilled and shaved smoothly with the surrounding joint edges, giving the floor joints a flat appearance. Shaving of excess EUCO QWIKjoint UVR can begin approximately 1 hour after placement, and up to 24 hours later, depending on jobsite conditions such as the concrete and ambient temperatures.

CLEAN-UP

EUCO SOLVENT or acetone may be used for clean-up of tools and equipment. Clean excess material before EUCO QWIKjoint UVR has cured. Cured material will require removal by mechanical means.

PRECAUTIONS/LIMITATIONS

- **Based on ACI 302 recommendations, joint fillers should be applied as late as possible after construction to allow for minimal additional slab shrinkage. Consult ACI 302 comments regarding concrete shrinkage, joint filling and user expectations.**
- One EUCLID UNIVERSAL COLOR PACK (EUCO Pack) may be added per 10 gal (37.85 L) unit of Neutral Base; mix into the "B" side.
- EUCO QWIKjoint UVR material and all application equipment should be kept at ambient temperatures of 50°F (10°C) or above.
- Surface and ambient temperature during applications should be between -20°F and 90°F (-29°C and 32°C)
- Do not use EUCO QWIKjoint UVR as an expansion joint sealant.
- Contact surfaces must be clean and dry for best adhesion.
- Joint edges must be thoroughly cleaned prior to filling, particularly if a floor sealer or densifier has been applied.
- Product may slightly discolor if constantly exposed to exterior UV radiation.
- In all cases, consult the Safety Data Sheet before use.

Rev. 02.17

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.